

Thermoplastic Elastomer 60° Shore A Thermoplastic Elastomer 80° Shore A

60° Shore A

ISO 868 Density: 1,09 g/cm ISO 1183 Pull Strength: 7,0 N/mm² **ISO 37** Tear stretch: 750% **ISO 37**

Pressure deformation rest: ASTM D 395-89 B

20% (72h / 23°C)

Pressure deformation rest: **ISO 815**

48% (22h / 70°C)

80° Shore A

ASTM D 2240 Density: 0,98 g/cm³ **ASTM D 792** Pull Strength: 9,5 N/mm² **ASTM D 412** Tear stretch: 650% ASTM D 412 Pressure deformation rest: ASTM D 395 26% (22h / 23°C) Pressure deformation rest: ASTM D 395

44% (22h / 70°C)

Working Temperature:

-10° to +55° C

Physical Characteristics


- Color stability
- UV Resistant
- Ozone Resistant
- Smoke barrier complying EN 1634-3

Paint Compatibility:

The material used in DEVENTER S quality is compatible with thinned acrylic paints and alkyd resin paints containing conventional solvents. Paint and coatings, of which the properties are unknown must be tested for compatibility in contact with the weather seals.

S 5717





Available colors

