

Thermoplastic Elastomer 93° Shore A Thermoplastic Elastomer Foam 23° Shore A

93° Shore A

- | | |
|---|-------------|
| - Density: 0,97 g/cm ³ | ASTM D 2240 |
| - Pull Strength: 14,0 N/mm ² | ASTM D 792 |
| - Tear stretch: 600% | ASTM D 412 |
| - Tear force: 7,2 N/mm ² | ASTM D 412 |
| - Pressure deformation rest: 39% (22h / 23°C) | ASTM D 412 |
| - Pressure deformation rest: 61% (22h / 70°C) | ASTM D 395 |

23° Shore A

- | | |
|---|---------------|
| - Density: 0,96 g/cm ³ | EN ISO 868 |
| - Pull Strength: 6,0 N/mm ² | EN ISO 1183-1 |
| - Tear stretch: 800% | ISO 37 |
| - Tear force: 0,8 N/mm ² | ISO 37 |
| - Pressure deformation rest: 10% (24h / 23°C) | ISO 815 |
| - Pressure deformation rest: 12% (72h / 23°C) | ISO 815 |
| - Pressure deformation rest: 23% (24h / 70°C) | ISO 815 |

Working Temperature:

-10° to +55° C


Physical Characteristics

- Color stability
- UV Resistant
- Ozone Resistant
- Smoke barrier complying EN 1634-3

Paint Compatibility:

The material used in DEVENTER S quality is compatible with thinned acrylic paints and alkyd resin paints containing conventional solvents. Paint and coatings, of which the properties are unknown must be tested for compatibility in contact with the weather seals.

SP 63



Available colors



Management System
ISO 9001:2008

www.tuv.com
ID 1100005114